

Silicone Rubber

Technical Data Sheet

SR 2XXU Series

SX0610-2023-02 V2

Description: This series is a premixed compound of silicone rubber with general purpose with good balanced properties for extrusion process, vulcanizing under heat after addition of a vulcanizing agent that could be chosen according to processing requirement.

Special properties:

- Good balanced mechanical properties for extrusion.
- Good appearance.
- Easy to process and demold, not sticky to rolls.
- Good stability up to 200°C.
- Slight replastification after prolonged storage.
- Wide range of reloading or blending.
- Bright colors easily obtained
- Vacuum-packed

Main applications:

- Extrusions such as seals, sheet, tube, etc.
- Molded articles, calendered sheet, etc.

Characteristics:

Type (according to GB/T 5576-1997).....VMQ
 Natural color.....translucent

Curing Condition:

After addition of 1.1% of 2,5-dimethyl-2-5-di(tert-butylperoxy) hexane (at 45%) and vulcanization for 10 min at 170°C.

Mechanical properties

Item	Testing Method	Unit	Technical Data					
			SR230U	SR240U	SR250U	SR260U	SR270U	SR280U
Appearance	Visual Observation		Translucent	Translucent	Translucent	Translucent	Translucent	Translucent
Density	ASTM D792	g/cm3	1.09	1.13	1.17	1.19	1.21	1.23
Hardness	ASTM D2240	Shore A	31	41	50	59	69	79
Tensile Strength	ASTM D412	Mpa	7.1	8.1	9.0	9.2	8.6	7.7
Elongation	ASTM D412	%	690	587	390	332	238	186
100% Modulus	ASTM D412	Mpa	0.59	0.81	1.39	1.99	3.35	3.52
Tear Strength	ASTM D624 Die B	N/mm	12	14	17	16	18	16
Rebound	ASTM D395 Method B	%	73.9	70.3	68.5	59.9	56.5	52

Packaging: 20 kg per cardboard boxes.

Storage and shelf life:

This series may be stored in its original unopened packaging at a temperature below 40°C for up to 12 months as from the date of manufacture.

For More Product Information, Please Visit Our Website: www.sanezen.com

Contact:

Plant Address: Baishou Road, North District of Xuan Zhou Economic Development Zone, Xuan Cheng City Anhui Province, China.

Commercial Address: Room 1606-1608, Boda Commercial Buildings, No. 11 Puhuitang Road Xuhui District, Shanghai, China 200030 Tel: +86 21 6487 9251 Fax: +86 21 5106 2693

E-mail: kevenwang@sanezen.com

Warning to the users:

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and is in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. Sanezen guarantees that its products comply with its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for given use. Determination of the suitability of product for the uses and applications contemplated by users and others shall be the sole responsibility of users. Users are responsible for ensuring compliance with local legislation and for obtaining the necessary certifications and authorisations. Users are requested to check that they are in possession of the latest version of this document and Sanezen is at their disposal to supply any additional information.